



Trojan **PROFESSIONAL**
Luxury Vinyl Planks

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Fax (03) 9371 2499

TEST REPORT

Client: Trojan Timbers Pty Ltd
PO Box 3363
Stafford DC QLD 4031

Test Number: 17-006429
Issue Date: 5/12/2017
Print Date: 5/12/2017

Sample Description Clients Ref: "Trojan Professional Luxury Vinyl Plank"
Vinyl flooring plank
Colour: Woodgrain
End Use: Flooring Covering
Nominal Composition: Vinyl
Nominal Mass per Unit Area/Density: 10kg/m²
Nominal Thickness: 5mm

AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 13/11/2017
Date Tested 01/12/2017

CHF Value	1	2	3	Mean
Length	6.9	6.9	6.5	6.8 kW/m ²
Width	7.7	-	-	- kW/m ²

Smoke Value	1	2	3	Mean
Length	98	28	123	83 %min
Width	67	-	-	- %min

Blistering Yes

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR



Australian Wool Testing Authority Ltd – trading as AWTA Product Testing

A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Trojan Timbers Pty Ltd
PO Box 3363
Stafford DC QLD 4031

Test Number: 17-006429
Issue Date: 5/12/2017
Print Date: 5/12/2017

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR